



PREMIUM CLEAR SELF-CROSSLINKING WB LACQUER

DESCRIPTION

Gemini's WBXL-03XX series is a single component, self-crosslinking, clear waterborne lacquer. It has very good hardness and durability, is water clear, and has excellent resistance to yellowing. For wood substrates only. For interior use only.

PRODUCT NUMBERS / SHEENS		COATING PROPERTIES	PREPARATION INSTRUCTIONS
WBXL-0390	Gloss	Viscosity: 30"-35" #3 Zahn @ 77° Weight Solids: 32.2-34.3% Volume Solids: 29.5-30.9% Weight/Gallon: 8.5-8.67 lbs./gal Coverage: 473-496 sq. ft. per gallon at one mil dry film thickness. VOC (reg./coating): 1.57-1.66 lbs./gal or 187.9-198.4 g/l VOC (act/material): .61-.63 lbs./gal or 73.2-75 g/l VOC Ratio: 0.2-0.23 lbs. VOC/lbs. Solids HAPS Ratio: 0.0 lbs. HAPS/lbs. Solids Dry Times: Air Dry: at 78° F, relative humidity 50% To touch: 10-12 minutes To handle: 15-20 minutes To sand/recoat: 35-45 minutes Force Dry: Flash: 10 minutes Bake: 30 min @ 105° F Cool down: 10 min Relative humidity will affect the speed of drying. Ideal conditions are 75° F or warmer at 50% humidity or less. Dry time will be faster at higher temperatures and lower humidity and equally slower at colder temperatures and higher humidity. Dry Film Thickness: <i>Maximum DFT for a complete system must not exceed 6 dry mils.</i> Shelf Life: 12 months @77° F if unopened and stored in a cool dry area. Always rotate stock. Storage: Protect product from freezing.	Reduction/Thinning*: Reduction is not necessary but may be required for certain types of application and equipment. Use water for reduction. Very little water is needed to reduce viscosity, typically no more than 5% by volume. Retarder: If a slower dry time is desired, or to improve flow and leveling, use SOL-0090 at levels not to exceed 4% by volume (5.1 oz per gallon). Maximum VOC when adding retarder as specified is < 275 grams per liter. *Thinning this material may result in increasing the VOC levels of this product. Refer to your local regulations before thinning. Approved Companion Products WBXLSS-0100 Premium Sanding Sealer <i>Note: These numbers represent actual control values on a smooth, sanded substrate. Spray techniques, texture, and sealing as well as film thickness may give different results on actual work, but they may be used for comparison. To the best of our knowledge, the above technical data is true and accurate at the date of issuance but is subject to change without prior notice.</i>
WBXL-0360	Semi Gloss		
WBXL-0330	Satin		
WBXL-0320	Dull		
WBXL-0310	Flat		
PRODUCT ADVANTAGES			
<ul style="list-style-type: none"> ➤ Low Odor ➤ Dries fast ➤ Water Clear ➤ Excellent Resistance To Yellowing* ➤ Durable Film ➤ Superb Flow And Leveling ➤ Minimal Grain Raise ➤ Low VOC And HAPs Free ➤ Formaldehyde Free ➤ Phthalate Free <p>* The coating will not protect the wood, lightly stained wood substrates, or pigmented basecoats from yellowing</p>			

August, 2021

The following supersedes any provision contained in the forms, letters and papers of your company. This product is designed and intended for professional application only. All products should be thoroughly tested under application conditions prior to use. The information contained herein is believed to be reliable. **HOWEVER, GEMINI MAKES NO WARRANTY CONCERNING THIS PRODUCT, WHETHER EXPRESS OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** UNDER NO CIRCUMSTANCES SHALL GEMINI BE LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL, OR ANY OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH OF WARRANTY, STRICT LIABILITY, OR ANY OTHER LEGAL THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. THE SOLE REMEDY OF THE BUYER AND THE SOLE LIABILITY OF GEMINI FOR ANY CLAIMS SHALL BE LIMITED TO THE BUYER'S PURCHASE PRICE OF THE PRODUCT WHICH IS THE SUBJECT OF THE CLAIM OR THE AMOUNT ACTUALLY PAID FOR SUCH PRODUCT, WHICHEVER IS LESS. TECHNICAL ADVICE FURNISHED BY GEMINI SHALL NOT CONSTITUTE AN EXPRESS WARRANTY, WHICH IS EXPRESSLY DISCLAIMED. ALL TECHNICAL ADVICE GIVEN IS ACCEPTED AT THE RISK OF THE BUYER. **CAUTION: DANGER! FLAMMABLE! VAPORS MAY CAUSE FLASH FIRE. VAPOR HARMFUL. HARMFUL OR FATAL IF SWALLOWED. INJURIOUS TO EYES. KEEP OUT OF THE REACH OF CHILDREN!** BEFORE using this product it is essential that the "Material Safety Data Sheet" describing the product as well as the "Product Label" be reviewed. If your company does not have such information or has any questions, contact the manufacturer.

PRODUCT DATA SHEET WBXL-03XX SERIES CONTINUED



Substrate preparation:

New wood: Remove any dirt, grease, glue or other contaminants. Moisture content of wood should be 7-9%. Sand to 150-180 grit. Proper sanding of wood is absolutely critical to achieve the best color development and adhesion of the coating to the substrate.

Old wood: Strip old finishes completely and remove all contaminants from the surface. Make sure the surface is dry, sand as required. Finish same as new wood.



Mixing Instructions:

Mix thoroughly before use. **DO NOT SHAKE!** Material may be mixed by hand or mechanical agitation at moderate speed.



Application:

Using conventional, HVLP, airless, or air assisted equipment, apply this product at 3-4 wet mils per coat. Let dry a minimum of 35-45 minutes. Sand with 280-320 grit, no-fill sandpaper and remove sanding dust with clean compressed air. This product must be sanded in between coats to ensure proper adhesion.

This product has been designed as a self-seal system. Typically we recommend a coating system comprised of 2-3 coats WBXL-03XX applied at 3-4 wet mils. If used with a sealer we recommend a coating system comprised of 1 coat of WBXLSS-0100 sealer applied at 3-4 wet mils per coat and 1-2 coats of WBXL-03XX. **Maximum dry film thickness of the complete system must not exceed 6 dry mils.**

This product must not be polluted with oil, solvent based paint or the like and should not be applied to metal surfaces. Application and drying conditions must be at temperatures of 60°F or above and at a humidity of less than 65%. Increased air flow and/or drying temperatures, including the use of infrared lighting for cure will significantly decrease dry times.



Recommended Tip Sizes:

Conventional Air	1.8-2.0mm
HVLP	1.9-2.2mm
Airless	10-15 thousandths
Air Assisted Airless-	11-15 thousandths



Precautions:

These products are intended for Professional use only. Do not proceed if you are planning on mixing with other finishing systems or other manufacturer's products. Gemini will not be held liable for finish failures due to the improper use of our products or deviation from our finishing recommendations

Equipment:

All equipment used with this product must have plastic, stainless steel, or Teflon fluid passages and wetted parts

Containers:

All containers used in conjunction with storage and/or application of this product should be stainless steel or plastic to avoid rust.

Clean up:

Use water to clean all equipment when material is in a liquid stage. Use 2:1 mixture of water and Butyl Cellosolve (SOL-0061) to remove semi-dried or dried coating. Dispose of in accordance with Federal, State, and Local regulation regarding pollution.

Care and cleaning of this finish: Use a mild dishwashing liquid and a damp cloth to remove food, grease, and other residue. Wipe dry. Do not use cleaners that contain ammonia, bleach, or abrasives as this may damage the finish.