



# DURALAQ<sup>®</sup>

## WATER WHITE SANDING SEALER

### 1C-203

#### Features

- 20% Solid Content
- Sands Easily
- Cost Savings
- Fast Drying
- Designed For Easy Spraying

#### General Description

Lenmar<sup>®</sup> DuraLaq<sup>®</sup> 1C-203 is a ready-to-spray, water white nitrocellulose sanding sealer designed for interior wood applications only. The primary benefits of this sealer include its clarity, ease of application, ease of repair, and flow/leveling characteristics. When properly applied this product offers good initial build and excellent adhesion on properly prepared wood surfaces. This product sands easily and powders nicely to provide a smooth sealed foundation for follow-on coats. DuraLaq<sup>®</sup> 1C-203 is compatible with any Lenmar<sup>®</sup> nitrocellulose lacquer topcoat. It is not recommended for use over pickle finishes or white stains.

#### Recommended For

Window & Door Trim, Fine Furniture, High End Interior Wood, Door Trim & Crown Molding, Interior Doors & Hand Rails.

#### Limitations

- It is not recommended for use over pickle finishes or white stains. Do not apply more than two topcoats.
- Entire system should not exceed 4 mils dry.

#### Product Information

<p><b>Colors — Standard:</b> Clear</p> <p><b>— Tint Bases:</b> N/A</p> <p><b>— Special Colors:</b> N/A</p> <p><b>Certification &amp; Qualifications:</b></p> <p>The products supported by this data sheet contain a maximum of 680 grams per liter VOC (5.7 lbs/gal.) excluding water &amp; exempt solvents.</p> <p>*Thinning this material may result in increasing the VOC levels of this product. Refer to your local regulations before thinning.</p> <table border="1" style="margin-left: auto; margin-right: auto;"> <thead> <tr> <th>VOC REGION</th> <th>COMPLIANT</th> </tr> </thead> <tbody> <tr> <td>FEDERAL</td> <td>YES</td> </tr> <tr> <td>OTC</td> <td>NO</td> </tr> <tr> <td>OTCII</td> <td>NO</td> </tr> <tr> <td>CARB</td> <td>NO</td> </tr> <tr> <td>CARB07</td> <td>NO</td> </tr> <tr> <td>UTAH</td> <td>NO</td> </tr> <tr> <td>AZMC</td> <td>YES</td> </tr> <tr> <td>SCAQMD</td> <td>NO</td> </tr> </tbody> </table> <p><b>Technical Assistance:</b> Available through your local authorized independent Lenmar dealer. For the location of the dealer nearest you, call 1-877-299-3600 or visit <a href="http://www.lenmar-coatings.com">www.lenmar-coatings.com</a></p>	VOC REGION	COMPLIANT	FEDERAL	YES	OTC	NO	OTCII	NO	CARB	NO	CARB07	NO	UTAH	NO	AZMC	YES	SCAQMD	NO	<p><b>Technical Data</b> <span style="float: right;"><b>Clear</b></span></p> <table border="1" style="width: 100%;"> <tr> <td>Vehicle Type</td> <td style="text-align: right;">Nitrocellulose</td> </tr> <tr> <td>Pigment Type</td> <td style="text-align: right;">N/A</td> </tr> <tr> <td>Weight Solids</td> <td style="text-align: right;">20% ± 1.0%</td> </tr> <tr> <td>Volume Solids</td> <td style="text-align: right;">14% ± 1.0%</td> </tr> <tr> <td>Coverage per Gallon at 1 mil DFT</td> <td style="text-align: right;">225 – 250 sq. ft.</td> </tr> <tr> <td>Recommended Film Thickness</td> <td style="text-align: right;"> <table border="0" style="width: 100%;"> <tr> <td style="width: 50%;">– Wet</td> <td style="text-align: right;">3 – 5 mils</td> </tr> <tr> <td>– Dry</td> <td style="text-align: right;">0.4 – 0.7 mils</td> </tr> </table> </td> </tr> </table> <p>Coverage calculation does not include spray loss or equipment inefficiency. Also allow for wood species, surface preparation, surface defects and porosity of substrate to affect spread rates.</p> <table border="1" style="width: 100%;"> <tr> <td rowspan="2">Dry Time @ 75 °F (23.8 °C) @ 50% RH</td> <td>– To Sand</td> <td style="text-align: right;">20 – 30 Minutes</td> </tr> <tr> <td>– To Recoat</td> <td style="text-align: right;">30 Minutes</td> </tr> </table> <p>High humidity and cool temperatures will result in longer dry and recoat times.</p> <table border="1" style="width: 100%;"> <tr> <td>Dries By</td> <td style="text-align: right;">Evaporation</td> </tr> <tr> <td>Viscosity</td> <td style="text-align: right;">25 – 28 Seconds (#2 Zahn)</td> </tr> <tr> <td>Flash Point</td> <td style="text-align: right;">25 °F (-3.9 °C)</td> </tr> <tr> <td>Gloss / Sheen</td> <td style="text-align: right;">N/A</td> </tr> <tr> <td>Surface Temperature at Application</td> <td style="text-align: right;"> <table border="0" style="width: 100%;"> <tr> <td style="width: 50%;">– Min.</td> <td style="text-align: right;">45 °F</td> </tr> <tr> <td>– Max.</td> <td style="text-align: right;">90 °F</td> </tr> </table> </td> </tr> <tr> <td>Thin With</td> <td style="text-align: right;">See Specifications Section</td> </tr> <tr> <td>Clean Up Thinner</td> <td style="text-align: right;">1A-406 or 1A-519 Lacquer Thinner</td> </tr> <tr> <td>Weight Per Gallon</td> <td style="text-align: right;">7.1 – 7.3 lbs.</td> </tr> <tr> <td>Storage Temperature</td> <td style="text-align: right;"> <table border="0" style="width: 100%;"> <tr> <td style="width: 50%;">– Min.</td> <td style="text-align: right;">50 °F</td> </tr> <tr> <td>– Max.</td> <td style="text-align: right;">90 °F</td> </tr> </table> </td> </tr> </table> <p style="text-align: center;"><b>Volatile Organic Compounds (VOC)</b></p> <p style="text-align: center;">668 Grams/Liter    5.57 Lbs./Gallon</p>	Vehicle Type	Nitrocellulose	Pigment Type	N/A	Weight Solids	20% ± 1.0%	Volume Solids	14% ± 1.0%	Coverage per Gallon at 1 mil DFT	225 – 250 sq. ft.	Recommended Film Thickness	<table border="0" style="width: 100%;"> <tr> <td style="width: 50%;">– Wet</td> <td style="text-align: right;">3 – 5 mils</td> </tr> <tr> <td>– Dry</td> <td style="text-align: right;">0.4 – 0.7 mils</td> </tr> </table>	– Wet	3 – 5 mils	– Dry	0.4 – 0.7 mils	Dry Time @ 75 °F (23.8 °C) @ 50% RH	– To Sand	20 – 30 Minutes	– To Recoat	30 Minutes	Dries By	Evaporation	Viscosity	25 – 28 Seconds (#2 Zahn)	Flash Point	25 °F (-3.9 °C)	Gloss / Sheen	N/A	Surface Temperature at Application	<table border="0" style="width: 100%;"> <tr> <td style="width: 50%;">– Min.</td> <td style="text-align: right;">45 °F</td> </tr> <tr> <td>– Max.</td> <td style="text-align: right;">90 °F</td> </tr> </table>	– Min.	45 °F	– Max.	90 °F	Thin With	See Specifications Section	Clean Up Thinner	1A-406 or 1A-519 Lacquer Thinner	Weight Per Gallon	7.1 – 7.3 lbs.	Storage Temperature	<table border="0" style="width: 100%;"> <tr> <td style="width: 50%;">– Min.</td> <td style="text-align: right;">50 °F</td> </tr> <tr> <td>– Max.</td> <td style="text-align: right;">90 °F</td> </tr> </table>	– Min.	50 °F	– Max.	90 °F
VOC REGION	COMPLIANT																																																																	
FEDERAL	YES																																																																	
OTC	NO																																																																	
OTCII	NO																																																																	
CARB	NO																																																																	
CARB07	NO																																																																	
UTAH	NO																																																																	
AZMC	YES																																																																	
SCAQMD	NO																																																																	
Vehicle Type	Nitrocellulose																																																																	
Pigment Type	N/A																																																																	
Weight Solids	20% ± 1.0%																																																																	
Volume Solids	14% ± 1.0%																																																																	
Coverage per Gallon at 1 mil DFT	225 – 250 sq. ft.																																																																	
Recommended Film Thickness	<table border="0" style="width: 100%;"> <tr> <td style="width: 50%;">– Wet</td> <td style="text-align: right;">3 – 5 mils</td> </tr> <tr> <td>– Dry</td> <td style="text-align: right;">0.4 – 0.7 mils</td> </tr> </table>	– Wet	3 – 5 mils	– Dry	0.4 – 0.7 mils																																																													
– Wet	3 – 5 mils																																																																	
– Dry	0.4 – 0.7 mils																																																																	
Dry Time @ 75 °F (23.8 °C) @ 50% RH	– To Sand	20 – 30 Minutes																																																																
	– To Recoat	30 Minutes																																																																
Dries By	Evaporation																																																																	
Viscosity	25 – 28 Seconds (#2 Zahn)																																																																	
Flash Point	25 °F (-3.9 °C)																																																																	
Gloss / Sheen	N/A																																																																	
Surface Temperature at Application	<table border="0" style="width: 100%;"> <tr> <td style="width: 50%;">– Min.</td> <td style="text-align: right;">45 °F</td> </tr> <tr> <td>– Max.</td> <td style="text-align: right;">90 °F</td> </tr> </table>	– Min.	45 °F	– Max.	90 °F																																																													
– Min.	45 °F																																																																	
– Max.	90 °F																																																																	
Thin With	See Specifications Section																																																																	
Clean Up Thinner	1A-406 or 1A-519 Lacquer Thinner																																																																	
Weight Per Gallon	7.1 – 7.3 lbs.																																																																	
Storage Temperature	<table border="0" style="width: 100%;"> <tr> <td style="width: 50%;">– Min.</td> <td style="text-align: right;">50 °F</td> </tr> <tr> <td>– Max.</td> <td style="text-align: right;">90 °F</td> </tr> </table>	– Min.	50 °F	– Max.	90 °F																																																													
– Min.	50 °F																																																																	
– Max.	90 °F																																																																	

May, 2022

## DuraLaq® Sanding Sealer 1C-203

**WARNING!** If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Informational Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

### Application

**ENTIRE SYSTEM SHOULD NOT EXCEED MORE THAN 4 MILS DRY. LENMAR® PRODUCTS ARE DESIGNED FOR INTERIOR USE, BY SPRAY APPLICATION ONLY.**

Over properly prepared interior wood surfaces, apply one coat of DuraLaq® 1C-203, let dry, then sand. Topcoat with desired sheen level using any of the DuraLaq® Series Lacquers. For additional resistance to moisture and chemicals, try the following Lenmar® Finishing Systems: Ultra UniLaq® Acrylic 1M-97X series. Do not apply more than two topcoats.

**ENTIRE SYSTEM SHOULD NOT EXCEED 4 MILS DRY.**

### Specifications

Moisture content of wood should be no higher than 9%. Wood must be free of surface contaminants. Final sand wood with 120 to 150-grit sandpaper, depending on species, and remove all dust. Mix DuraLaq® 1C-203 thoroughly and reduce as necessary with Lenmar® 1A-519 or 1A-406 lacquer thinners, to achieve proper atomization. Apply one coat at 3-4 wet mils, allow to dry, then sand with 280-320 grit silicon carbide sandpaper. Select the sheen required from any of the DuraLaq® Series products, mix well and apply at least two coats. These products may be reduced with 1A-406 or 1A-519 or use 1A-114 retarder if necessary to prevent blushing. Do not reduce if doing so would violate any VOC regulations. Check with equipment manufacturer for proper settings to achieve the optimum atomization. Read label and SDS for additional information and warnings.

### Clean Up

Clean equipment with Lenmar® 1A-406 or 1A-519 Lacquer Thinner.

### Environmental Health & Safety Information

#### DANGER!

Harmful if inhaled

Causes skin irritation

Causes serious eye damage

Suspected of damaging fertility or the unborn child

May cause drowsiness or dizziness

May cause damage to organs through prolonged or repeated exposure

May be fatal if swallowed and enters airways

Highly flammable liquid and vapor

**Prevention:** Obtain special instructions before use. Do not handle until all safety precautions have been read and understood. Use personal protective equipment as required. Use only outdoors or in a well-ventilated area. Wash face, hands and any exposed skin thoroughly after handling. Do not breathe dust/fume/ gas/ mist/ vapors/ spray. Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking. Keep container tightly closed. Ground/bond container and receiving equipment. Use explosion-proof electrical/ventilating/ lighting/equipment. Use only non-sparking tools. Take precautionary measures against static discharge. Keep cool.

**Response:** IF exposed or concerned: Get medical advice/attention  
IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. Immediately call a POISON CENTER or doctor/physician.  
If skin irritation occurs: Get medical advice/attention. IF ON SKIN (or hair): Remove/Take off immediately all contaminated clothing. Rinse skin with water/shower. Wash contaminated clothing before reuse. IF INHALED: Remove victim to fresh air and keep at rest in a position comfortable for breathing. IF SWALLOWED: Immediately call a POISON CENTER or doctor/ physician. Do NOT induce vomiting. In case of fire: Use CO<sub>2</sub>, dry chemical, or foam for extinction.

**Storage:** Store locked up. Store in a well-ventilated place, keep container tightly closed.

**Disposal:** Dispose of contents/container to an approved waste disposal plant.



**WARNING** Cancer and Reproductive Harm—  
[www.P65warnings.ca.gov](http://www.P65warnings.ca.gov)

**KEEP OUT OF REACH OF CHILDREN  
INTENDED FOR PROFESSIONAL USE ONLY  
FOR WOOD SUBSTRATES ONLY  
FOR INTERIOR USE ONLY**

This product is intended for Shop or OEM applications. This product may also be compliant under Architectural and Industrial Maintenance regulations in some jurisdictions for field application to stationary structures. Check local regulations.

**READ ALL DIRECTIONS BEFORE USE.  
UNDERSTAND ALL DANGERS WITH THIS  
PRODUCT PRIOR TO USE.**

**Refer to Safety Data Sheet for additional  
health and safety information.**