



DURALAQ-WB[®]

WATERBORNE ACRYLIC SELF-SEALING CLEAR FINISH 1WB-10X

Features

- Exceptional Solids
- Ready To Spray Viscosity
- Non-Yellowing
- Single Component
- Four Sheen Levels

General Description

Lenmar[®] DuraLaq-WB[®] 1WB-10X Series of Waterborne Finishes are the natural choice where the uses of traditional solvent-borne lacquers are not practical. Additionally, DuraLaq-WB[®] products easily clean-up with water and they form a durable non-yellowing finish all in a ready to spray viscosity. Use of waterborne systems requires spray equipment to be all stainless steel, verify design and function before use with waterborne products. Properly maintained equipment and lines will help to eliminate defects in coating performance.

Recommended For

Kitchen Cabinets, Wood and Door Trim, Baseboards and Moldings, Interior Shutters, Displays

Limitations

- For best results, apply at room temperature above 68° F.
- Entire system not to exceed more than 5mils dry.

Product Information

Colors — Standard:		Technical Data		Clear/Gloss																		
Clear		Vehicle Type		Modified Acrylic																		
1WB-102 Dull Rubbed	1WB-104 Satin	Pigment Type		N/A																		
1WB-106 Semi-Gloss	1WB-109 Gloss	Weight Solids		28% ± 1.0%																		
— Tint Bases:		Volume Solids		26% ± 1.0%																		
N/A		Coverage per Gallon at 1 mil DFT		417 – 425 Sq. Ft.																		
— Special Colors:		Recommended Film Thickness		– Wet 3 - 5 mils – Dry 0.9 – 1.25 mils																		
N/A		Coverage calculation does not include spray loss or equipment inefficiency. Also allow for wood species, surface preparation, surface defects and porosity of substrate to affect spread rates.																				
Certification & Qualifications:		Dry Time @ 75 °F		– To Sand 30 – 35 Minutes																		
The products supported by this data sheet contain a maximum of 550 grams per liter VOC (4.59 lbs/gal.) excluding water and exempt solvents.		@ 50% RH		– To Recoat 35 – 45 Minutes																		
*Thinning this material may result in increasing the VOC levels of this product. Refer to your local regulations before thinning.		High humidity and cool temperatures will result in longer dry and recoat times.																				
<table border="1"> <thead> <tr> <th>VOC REGION</th> <th>COMPLIANT</th> </tr> </thead> <tbody> <tr><td>FEDERAL</td><td>YES</td></tr> <tr><td>OTC</td><td>YES</td></tr> <tr><td>OTCII</td><td>NO</td></tr> <tr><td>CARB</td><td>YES</td></tr> <tr><td>CARB07</td><td>NO</td></tr> <tr><td>UTAH</td><td>NO</td></tr> <tr><td>AZMC</td><td>YES</td></tr> <tr><td>SCAQMD</td><td>NO</td></tr> </tbody> </table>		VOC REGION	COMPLIANT	FEDERAL	YES	OTC	YES	OTCII	NO	CARB	YES	CARB07	NO	UTAH	NO	AZMC	YES	SCAQMD	NO	Dries By		Coalescence
VOC REGION	COMPLIANT																					
FEDERAL	YES																					
OTC	YES																					
OTCII	NO																					
CARB	YES																					
CARB07	NO																					
UTAH	NO																					
AZMC	YES																					
SCAQMD	NO																					
		Viscosity		38 – 42 Seconds (#2 Zahn)																		
		Flash Point		>200 °F																		
		Gloss / Sheen		Dull Rubbed/Satin Semi-Gloss/High Gloss																		
		Surface Temperature at Application		– Min. 68 °F for best results – Max. 90 °F																		
		Thin With		Not required																		
		Clean Up Thinner		Use distilled water immediately and flush system with isopropyl alcohol or a blend of water and butyl cellosolve																		
		Weight Per Gallon		8.4 – 8.6 lbs																		
		Storage Temperature		– Min. 50 °F – Max. 90 °F																		
		Volatile Organic Compounds (VOC)																				
		378 Grams/Liter		3.16 Lbs./Gallon																		
Technical Assistance:																						
Available through your local authorized independent Lenmar dealer. For the location of the dealer nearest you, call 1-877-299-3600 or visit www.lenmar-coatings.com																						

May, 2022

◇ Reported values are for Clear/Gloss. Contact your dealer/distributor for values of other bases or colors

DuraLaq-WB® Waterborne Acrylic Self-Sealing Clear Finish 1WB-10X

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Informational Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Application

ENTIRE SYSTEM SHOULD NOT EXCEED MORE THAN 5 MILS DRY. LENMAR PRODUCTS ARE DESIGNED FOR INTERIOR USE, BY SPRAY APPLICATION ONLY.

Over properly prepared interior wood surfaces apply one coat of DuraLaq-WB® 1WB-10X waterborne as a sealer in a 2-3 mil coat. Allow to dry and sand with silicon carbide 280-320 grit sandpaper. Topcoat with the desired sheen level selected from the 1WB-10X Series. Apply two coats, by spray only, at 3-5 mils each. Allow to fully and scuff sand between all coats. Do not exceed more than two topcoats (3 coats total). Keep from freezing. For best results, apply at room temperature above 68°F.

ENTIRE SYSTEM NOT TO EXCEED MORE THAN 5 MILS DRY.

Specifications

Moisture content of wood should be no higher than 9%. Wood must be free of surface contaminants. Final sand wood no finer than 150-grit sandpaper, and remove all sanding dust. Mix thoroughly and apply by spray only. Check with equipment manufacturer for ideal settings to achieve proper atomization. Make sure equipment is designed for use with waterborne products. Follow all recommended maintenance procedures. After first coat has dried, sand with 280-320 grit, non-stearated, silicon carbide paper prior to applying final two coats. Apply in a self-seal finish, 3 coats. Variations of temperature and humidity may affect normal dry times. To promote adhesion, scuff sand between coats and remove sanding dust. Do not use steel wool. Use distilled water, in small amounts, if reduction is necessary. Read label and SDS for additional information and warnings

Clean Up

Use distilled water immediately and flush system with isopropyl alcohol or a blend of water and butyl cellosolve.

Environmental Health and Safety Information

Not a hazardous substance or mixture according to the Globally Harmonized System (GHS)

Keep container closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with local regulations. Wash thoroughly after handling. Refer to Safety Data Sheet for additional health and safety information.



WARNING Cancer and Reproductive Harm—
www.P65warnings.ca.gov

This document represents hazards of the product referenced above. Refer to the individual Safety Data Sheet for hazards of the specific product you will be using.

**KEEP FROM FREEZING
FOR PROFESSIONAL USE ONLY
KEEP OUT OF REACH OF CHILDREN**

**FOR WOOD SUBSTRATES ONLY
FOR INTERIOR USE ONLY**

This product is intended for Shop or OEM application only.

This product may be compliant under Architectural and Industrial Maintenance regulations in some jurisdictions when field applied to stationary structures. This product may also be Shop or OEM applied. Check local regulations.

**READ ALL DIRECTIONS BEFORE USE.
UNDERSTAND ALL DANGERS WITH THIS
PRODUCT PRIOR TO USE.**

**Refer to Safety Data Sheet for
additional health and safety information.**