



PRECATALYZED LACQUERS

Clear & White • 680 VOC Series



A furniture and entry-level kitchen cabinet grade system formulated with high quality synthetic resins, the finest grades of nitrocellulose and represents an intermediate step between conventional lacquer and conversion varnish. Use on any interior wood surface where enhanced durability, water and chemical resistance are indicated.

PRODUCT ADVANTAGES

- Water Clear
- Self-Sealing
- Tint Strength Controlled
- Excellent Flow and Level
- Meets or Exceeds KCMA Standards
- Available in Aerosol for Touch Up or Small Applications



CLEAR PRECATALYZED LACQUER

210-0215 – Precatalyzed Sealer

510-0050 – Gloss

510-0051 – Semi-Gloss

510-0052 – Satin

510-0053 – Flat

510-0062 – Dull (20°)

WHITE PRECATALYZED LACQUER

110-0016 – Pigmented White Sealer

410-0075 – Gloss

410-0076 – Semi-Gloss

410-0077 – Satin

410-0078 – Dull (20°)



PRECATALYZED LACQUERS

Clear & White • 680 VOC Series

COATING PROPERTIES AND APPLICATION PARAMETERS



CLEAR PRECATALYZED LACQUER

210-0215 – Precatalyzed Sealer
510-0050 – Gloss
510-0051 – Semi-Gloss
510-0052 – Satin
510-0053 – Flat
510-0062 – Dull (20°)

Viscosity

210-0215 – 21 #2 Zahn
510-0050, 51, 52, 53, 62 – 27 #2 Zahn

Weight Solids

210-0215 – 22%
510-0050, 51, 52, 53, 62 – 28%

Volume Solids

210-0215 – 16%
510-0050, 51, 52, 53, 62 – 20%

Dry Time to Touch

5-8 minutes

Dry Time to Handle

15-25 minutes

Dry Time to Sand

30-45 minutes

Max Dry Film Thickness

DFT should not exceed 3 mils

*Thinning or Retarding

Thinning: SOL-9011 – 10%
Retarding: SOL-9012 – 5%

Tinting

844 Colorants

Tip Sizes

Conventional 1.3 – 1.8mm
HVLP 1.3 – 1.8mm
Airless 0.010 – 0.015
Air Assisted Airless 0.011 – 0.015



WHITE PRECATALYZED LACQUER

110-0016 – Primer
410-0075 – Gloss
410-0076 – Semi-Gloss
410-0077 – Satin
410-0078 – Dull (20°)

Viscosity

110-0016 – 25 #2 Zahn
410-0075, 76, 77, 78 – 32 #4 Ford

Weight Solids

110-0016 – 50%
410-0075, 76, 77, 78 – 37%

Volume Solids

110-0016 – 30%
410-0075, 76, 77, 78 – 22%

Dry Time to Touch

5-7 minutes

Dry Time to Handle

15-25 minutes

Dry Time to Sand

30-45 minutes

Max Dry Film Thickness

DFT should not exceed 3 mils

*Thinning or Retarding

Thinning: SOL-9011 – 10%
Retarding: SOL-9012 – 5%

Tinting

844 up to 4 ounces

Tip Sizes

Conventional 1.3 – 1.8mm
HVLP 1.3 – 1.8mm
Airless 0.010 – 0.015
Air Assisted Airless 0.011 – 0.015

**Any adjustments made to these products may result in increased VOC levels. Refer to your local regulations for specific guidelines.*



for more information regarding Gemini "The Professional's Choice"

800.262.5710 or visit www.gemini-coatings.com



Gemini "The Professional's Choice"
is a Division of Gemini Industries

01/2018