

PRODUCT DATA SHEET

275 VOC Black Lacquer Sealer

DESCRIPTION

This black pigmented lacquer sealer exhibits excellent hide, build, and sanding qualities, and has been specifically designed to be used with our 275 VOC black lacquer topcoats for finishing doors, moldings, trim, and other interior woodwork projects that do not require significant moisture resistance. For wood substrates only. For interior use only.

Product Numbers / Sheens	COATING PROPERTIES	PREPARATION INSTRUCTIONS
400-2400	Viscosity: 16-18 #2 Zahn Weight Solids: 28.3% Volume Solids: 15% Weight/Gallon: 7.46 lb./gal Coverage: 298.6 sq. ft. per gallon at one mil dry film thickness.	Reduction: This product is supplied ready to spray. No thinning is recommended.
PRODUCT ADVANTAGES > 275 VOC Compliant	VOC (coating): 1.82 lb./gl. or 218.g/l VOC (material): .38 lb./gl. or 45.4 g/l VOC Ratio: 0.18 lb. VOC/lb. solids HAPS Ratio: 0.0	
 Ready To Spray Excellent Sandability 	Dry Times: Air Dry: at 78°F, relative humidity 50% To touch: 6 minutes To Handle: 15 minutes To sand/recoat: 30 minutes	
> Low VOC	Relative humidity will affect the speed of drying. Ideal conditions are 75°F or warmer at 50% humidity or less. Dry time will be faster at higher temperatures and lower	
➢ Zero HAPs	humidity and equally slower at colder temperatures and higher humidity.	
➢ Non photo chemically Reactive	Dry Film Thickness: For optimal results, the DFT for this primer should be between .6-1.2 mils. Please refer to	Approved Companion Products 400-24XX Black Lacquer Series
≻ Phthalate Free	the PDS for the specific topcoat you are using for maximum DFT for the complete system.	
	Pot Life: N/A	
	Shelf Life: 24 months @ 77° F if unopened and stored in a cool dry area. Always rotate stock.	Note: These numbers represent actual control values on a smooth, sanded substrate. Spray techniques, texture, and sealing as well as film thickness may give
	Storage: Keep away from heat or sparks.	texture, and seating as well as firm thickness may give different results on actual work, but they may be used for comparison. To the best of our knowledge, the above technical data is true and accurate at the date of issuance but is subject to change without prior notice.

February, 2023

The following supersedes any provision contained in the forms, letters and papers of your company. This product is designed and intended for professional application only. All products should be thoroughly tested under application conditions prior to use. The information contained herein is believed to be reliable. HOWEVER, GEMINI MAKES NO WARRANTY CONCERNING THIS PRODUCT, WHETHER EXPRESS OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. UNDER NO CIRCUMSTANCES SHALL GEMINI BE LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL, OR ANY OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH OF WARRANTY, STRICT LIABILITY, OR ANY OTHER LEGAL THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. THE SOLE REMEDY OF THE BUYER AND THE SOLE LIABLE TOR SPECIAL BE UNITED TO THE SUBJECT OF THE CLAIM OR THE MOUNT ACTUALLY PAID FOR SUCH PRODUCT, WHICHEVER IS LESS. TECHNICAL ADVICE FURNISHED BY GEMINI SHALL NOT CONSTITUTE AN EXPRESS WARRANTY, WHICH IS EXPRESSLY DISCLAIMED. ALL TECHNICAL ADVICE GIVEN IS ACCEPTED AT THE RISK OF THE BUYER. CAUTION: DANGER! FLAMMABLE! VAPORS MAY CAUSE FLASH FIRE. VAPOR HARMFUL. HARMFUL OR FATAL IF SWALLOWED. INJURIOUS TO EYES. KEEP OUT OF THE REACH OF CHILDREN! BEFORE using this product it is essential that the "Material Safety Data Sheet" describing the product as well as the "Product Label" be reviewed. If your company does not have such information or has any questions, contact the manufacturer.

PRODUCT DATA SHEET 400-2400 CONTINUED



A **I**A Substrate preparation:

New wood: Remove any dirt, grease, glue or other contaminants. Moisture content of wood should be 7-9%. Sand wood to 150-180 grit. Proper sanding of wood is absolutely critical to achieve the best color development and adhesion of the coating to the substrate.

Old wood: Strip old finishes completely and remove all contaminants from the surface. Make sure the surface is dry, sand as required. Finish same as new wood.



Mixing Instructions:

Mix material thoroughly before and during use. Material may be mixed by hand or mechanical agitation at moderate speed.



Application:

Using conventional, HVLP, airless, or air assisted equipment, apply this product at 3-4 wet mils per coat. Let dry a minimum of 30 minutes. Sand with 280-320 grit, no-fill sandpaper and remove sanding dust with clean compressed air, or tack rag.

We recommend a coating system comprised of one coat of sealer applied at 3-4 mils wet film build and 2 coats of topcoat applied at 3-4 mils wet film build (see approved companion products section). Refer to the Product Data Sheet for the topcoat for maximum dry film thickness recommendations.



Recommended Tip Sizes:Conventional Air1.3-1.8 mmHVLP1.5-1.9 mmAirless10-13 thousandthsAir Assisted Airless-10-13 thousandths



These products are intended for Professional use only. Do not proceed if you are planning on mixing with other finishing systems or other manufacturer's products. Gemini will not be held liable for finish failures due to the improper use of our products or deviation from our finishing recommendations

Equipment:

All equipment used with this product must have plastic, stainless steel, or Teflon fluid passages and wetted parts

Containers:

We supply this material in a lined container. All containers used in conjunction with storage and/or application of this product must be stainless steel, plastic, or otherwise acid resistant.

Clean up:

Use SOL-0020 Acetone, or SOL-9032 Zero VOC Lacquer Thinner to clean up all equipment. Dispose of in accordance with Federal, State, and Local regulation regarding pollution.

Care and cleaning of this finish: Use a mild dishwashing liquid and a damp cloth to remove food, grease, and other residue. Wipe dry. Do not use cleaners that contain ammonia, bleach, or abrasives as this may damage the finish.