

## 275 VOC High Build Water Clear Lacquer

### DESCRIPTION

This series is a higher build version of our 275 VOC water clear nitrocellulose lacquer system designed for finishing doors, moldings, trim, and other interior woodwork projects that do not require significant moisture resistance. These coatings have been formulated with state-of-the-art, clear, color stable resins, and are prepared at application viscosity. This is a preferred system for light or natural stains, or most situations that require a topcoat with low color and exceptional clarity. For wood substrates only. For interior use only.

PRODUCT NUMBERS / SHEENS	COATING PROPERTIES	PREPARATION INSTRUCTIONS
700-1290 Gloss 700-1260 Semi-Gloss 700-1230 Satin 700-1220 Dull 700-1210 Flat	<p><b>Viscosity:</b> 22 #2 Zahn  <b>Weight Solids:</b> 26.5 %  <b>Volume Solids:</b> 19.5 %  <b>Weight/Gallon:</b> 7.84-7.98 lb./gal  <b>Coverage:</b> 309 sq. ft. per gallon at one mil dry film thickness.  <b>VOC (coating):</b> 2.26-2.29 lbs./gl. or 270-274 g/l  <b>VOC (material):</b> 0.56 lb./gl. or 68 g/l  <b>VOC Ratio:</b> 0.31-0.32 lb. VOC/lb. solids  <b>HAPs Ratio:</b> Zero lb. HAPs/lb. solids</p> <p><b>Dry Times:</b>  <b>Air Dry:</b> at 78°F, relative humidity 50%            To touch: 8 minutes            To Handle: 15 minutes            To sand/recoat: 30 minutes</p> <p>Relative humidity will affect the speed of drying. Ideal conditions are 75°F or warmer at 50% humidity or less. Dry time will be faster at higher temperatures and lower humidity and equally slower at colder temperatures and higher humidity.</p> <p><b>Dry Film Thickness:</b>            Total DFT for the complete coating system should not exceed 5 mils.</p> <p><b>Pot Life:</b> N/A</p> <p><b>Shelf Life:</b> 24 months @ 77° F if unopened and stored in a cool dry area. Always rotate stock.  <b>Storage:</b> Keep away from heat or sparks.</p>	<p><b>Reduction:</b>            This product is supplied ready to spray. No thinning is recommended.</p> <p><b>Approved Companion Products</b>            700-1200 High Build Water Clear Sealer</p> <p><i>Note: These numbers represent actual control values on a smooth, sanded substrate. Spray techniques, texture, and sealing as well as film thickness may give different results on actual work, but they may be used for comparison. To the best of our knowledge, the above technical data is true and accurate at the date of issuance but is subject to change without prior notice.</i></p>
PRODUCT ADVANTAGES		
<ul style="list-style-type: none"> <li>➤ Low VOC</li> <li>➤ HAPs Free</li> <li>➤ Spray Viscosity</li> <li>➤ High Quality</li> <li>➤ Non Photo Chemically Reactive</li> <li>➤ Phthalate Free</li> </ul>		

February, 2023

The following supersedes any provision contained in the forms, letters and papers of your company. This product is designed and intended for professional application only. All products should be thoroughly tested under application conditions prior to use. The information contained herein is believed to be reliable. **HOWEVER, GEMINI MAKES NO WARRANTY CONCERNING THIS PRODUCT, WHETHER EXPRESS OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** UNDER NO CIRCUMSTANCES SHALL GEMINI BE LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL, OR ANY OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH OF WARRANTY, STRICT LIABILITY, OR ANY OTHER LEGAL THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. THE SOLE REMEDY OF THE BUYER AND THE SOLE LIABILITY OF GEMINI FOR ANY CLAIMS SHALL BE LIMITED TO THE BUYER'S PURCHASE PRICE OF THE PRODUCT WHICH IS THE SUBJECT OF THE CLAIM OR THE AMOUNT ACTUALLY PAID FOR SUCH PRODUCT, WHICHEVER IS LESS. TECHNICAL ADVICE FURNISHED BY GEMINI SHALL NOT CONSTITUTE AN EXPRESS WARRANTY, WHICH IS EXPRESSLY DISCLAIMED. ALL TECHNICAL ADVICE GIVEN IS ACCEPTED AT THE RISK OF THE BUYER. **CAUTION: DANGER! FLAMMABLE! VAPORS MAY CAUSE FLASH FIRE. VAPOR HARMFUL. HARMFUL OR FATAL IF SWALLOWED. INJURIOUS TO EYES. KEEP OUT OF THE REACH OF CHILDREN!** BEFORE using this product it is essential that the "Material Safety Data Sheet" describing the product as well as the "Product Label" be reviewed. If your company does not have such information or has any questions, contact the manufacturer.



**Substrate preparation:**

**New wood:** Remove any dirt, grease, glue or other contaminants. Moisture content of wood should be 7-9%. Sand wood to 150-180 grit. Proper sanding of wood is absolutely critical to achieve the best color development and adhesion of the coating to the substrate.

**Old wood:** Strip old finishes completely and remove all contaminants from the surface. Make sure the surface is dry, sand as required. Finish as new work.



**Mixing Instructions:**

Mix material thoroughly before and during use. Material may be mixed by hand or mechanical agitation at moderate speed.



**Application:**

Using conventional, HVLP, airless, or air assisted equipment, apply this product at 3-4 wet mils per coat. Let dry a minimum of 45 minutes. Sand with 280-320 grit, no-fill sandpaper and remove sanding dust with clean compressed air, or tack rag.

This product should be used in conjunction with 700-1200, 275 VOC High Build Water Clear Lacquer Sealer for best results. We recommend a coating system comprised of one coat of 700-1200 applied at 3-4 mils wet film build and 2 coats of topcoat applied at 3-4 mils wet film build. Maximum dry film thickness of the complete system must not exceed 5 dry mils.



**Recommended Tip Sizes:**

Conventional Air	1.3-1.8 mm
HVLP	1.5-1.9 mm
Airless	10-13 thousandths
Air Assisted Airless-	10-13 thousandths



**Precautions:**

These products are intended for Professional use only. Do not proceed if you are planning on mixing with other finishing systems or other manufacturer's products. Gemini will not be held liable for finish failures due to the improper use of our products or deviation from our finishing recommendations

**Equipment:**

All equipment used with this product must have plastic, stainless steel, or Teflon fluid passages and wetted parts

**Containers:**

We supply this material in a lined container. All containers used in conjunction with storage and/or application of this product must be stainless steel, plastic, or otherwise acid resistant.

**Clean up:**

Use SOL-0020 Acetone, or SOL-9032 Zero VOC Lacquer Thinner to clean up all equipment. Dispose of in accordance with Federal, State, and Local regulation regarding pollution.

**Care and cleaning of this finish:** Use a mild dishwashing liquid and a damp cloth to remove food, grease, and other residue. Wipe dry. Do not use cleaners that contain ammonia, bleach, or abrasives as this may damage the finish.