

# PRODUCT DATA SHEET

# ASTERIA White Conversion Varnish

### DESCRIPTION

ASTERIA White is a superior performance conversion varnish that has been specifically designed for kitchen and bathroom cabinetry, architectural millwork, and any other interior woodwork which demands superior flexibility, while maintaining excellent UV stability, water, and chemical resistance. ASTERIA White is super high solids and in conjunction with ASTERIA White or Neutral Primer/Surfacers, is the perfect solution for finishing MDF. For wood substrates only. For interior use only.

## PRODUCT NUMBERS / SHEENS

ASTW-1090 Gloss

ASTW-1060 Semi-Gloss

ASTW-1030 Satin

ASTW-1020 Dull

ASTW-1010 Flat

#### PRODUCT ADVANTAGES

- ➤ Super High Solids
- No Reduction Needed
- Excellent UV Resistance
- Superior Flexibility
- Excellent Resistance To Metal Marking
- Exceptional Water And Chemical Resistance
- Containers Are Short Filled To Allow For Tinting, And The Addition Of Catalyst
- Exceeds KCMA Performance Requirements When Applied To Manufacturer's Specifications
- ➤ Low VOC
- ➤ Low HAPs
- > Non Photo Chemically Reactive
- ➤ Pthalate Free

Note: These numbers represent actual control values on a smooth, sanded substrate. Spray techniques, texture, and sealing as well as film thickness may give different results on actual work, but they may be used for comparison. To the best of our knowledge, the above technical data is true and accurate at the date of issuance but is subject to change without prior notice.

February, 2023

# COATING PROPERTIES

Viscosity: 26-30 #4 Ford Weight Solids: 60.6-64.6% Volume Solids: 44.8-48.6% Weight/Gallon: 9.8-10.2 lbs./gal

Coverage: 718-779.1sq. ft. per gallon at one

mil dry film thickness.

VOC (reg./coating): 3.5-3.8 lbs./gl. or 423.8-

450.9 a/l

VOC (act/material): 3.5-3.6 lbs./gl. or 414.2-

433.7 g/l

VOC Ratio: 0.5-0.6 lbs.VOC/lbs. Solids HAPS Ratio: 0.05-0.058 lbs. HAPS/lbs.

Solids

# Dry Times:

Air Dry: at 78° F, relative humidity 50%

To touch: 10-12 minutes To handle: 20-30 minutes To sand/recoat: 50-60 minutes

Force Dry:

Flash: 8-10 minutes Bake:15 min @ 110° F Cool down: 15 min

Stack immediately after cool down

Relative humidity will affect the speed of drying. Ideal conditions are 75°F or warmer at 50% humidity or less. Dry time will be faster at higher temperatures and lower humidity and equally slower at colder temperatures and higher humidity.

**Dry Film Thickness:** Maximum DFT for a complete system must not exceed 7 dry mils.

Pot Life: 16 hours @ 77° F in a sealed

**Shelf Life Un-Catalyzed:** 12 months @77° F if unopened, and stored in a cool dry area.

Always rotate stock.

Storage: Keep away from heat or sparks.

# PREPARATION INSTRUCTIONS

Catalyzation:

Using CAT10-0700: Mix 100 parts ASTW-10XX to 11 parts CAT10-0700 Catalyst (11% by volume)

For gallon containers-Add one pre-measured 11.6 oz. bottle of CAT10-0700 per short-filled

gallon

For 5 gallon pails. Add 58 oz of CAT10-0700 per short-filled pail.

Gallon *Fill level is 106 oz.,* Five Gallon *Fill level is 530 oz.* 

Tinting: This product may be tinted up to 6 oz per gal with Chromaflo 844 colorants. **Do not** use umber pigments. Never tint with Universal Colorants that contain Glycol.

NOTE: DO NOT add more than the recommended amount of catalyst! This will not make the product cure faster or harder and may cause cracking, haziness, gloss issues, and will affect the integrity of the final product.

# Reduction:

**Important:** Always catalyze *BEFORE* reducing!

**Thinning:** This product is supplied ready to spray (after catalyzation). If needed due to conditions in your facility, use SOL-9059 HAPs Free Reducer or SOL-9011 HAPs Free Thinner at levels not to exceed 10% by volume.\*

**Retarder:** If a slower dry time is desired, use SOL-9012 Haps Free Retarder at levels not to exceed 4% by volume.\*

\*Thinning this material may result in increasing the VOC levels of this product. Refer to your local regulations before thinning.

# **Approved Companion Products**

ACVP-8000 ASTERIA Primer/Surfacer ANP-8500 ASTERIA Neutral Primer/Surfacer CVP-1000 PRESIDIO White Vinyl Primer AFCVRS-02XX ASTERIA Clear CV UCV-00XX Gemvar Clear CV

The following supersedes any provision contained in the forms, letters and papers of your company. This product is designed and intended for professional application only. All products should be thoroughly tested under application conditions prior to use. The information contained herein is believed to be reliable. HOWEVER, GEMINI MAKES NO WARRANTY CONCERNING THIS PRODUCT, WHETHER EXPRESS OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. UNDER NO CIRCUMSTANCES SHALL GEMINI BE LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL, OR ANY OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH OF WARRANTY, STRICT LIABILITY, OR ANY OTHER LEGAL THEORY, ARSING OUT OF THE USE OR HANDLING OF THIS PRODUCT. THE SOLE REMEDY OF THE BUYER AND THE SOLE LIABILITY OF GEMINI FOR ANY CLAIMS SHALL BE LIMITED TO THE BUYER'S PURCHASE PRICE OF THE PRODUCT WHICH IS THE SUBJECT OF THE CLAIM OR THE AMOUNT ACTUALLY PAID FOR SUCH PRODUCT, WHICHEVER IS LESS. TECHNICAL ADVICE FUNSHED BY GEMINIS SHALL NOT CONSTITUTE AN EXPRESS WARRANTY, WHICH IS EXPRESSLY DISCLAIMED. ALL TECHNICAL ADVICE GIVEN IS ACCEPTED AT THE RISK OF THE BUYER. CAUTION: DANGER! FLAMMABLE! VAPORS MAY CAUSE FLASH FIRE. VAPOR HARMFUL. HARMFUL OR FATAL IF SWALLOWED. INJURIOUS TO EYES. KEEP OUT OF THE REACH OF CHILDREN! BEFORE using this product it is essential that the "Material Safety Data Sheet" describing the product as well as the "Product Label" be reviewed. If your company does not have such information or has any questions, contact the manufacturer.



# PRODUCT DATA SHEET ASTW-10XX CONTINUED





### Substrate preparation:

**New wood:** Remove any dirt, grease, glue or other contaminants. Moisture content of wood should be 7-9%. Sand to 150-180 grit. Proper sanding of wood is absolutely critical to achieve the best color development and adhesion of the coating to the substrate.

**Old wood**: Strip old finishes completely and remove all contaminants from the surface. Make sure the surface is dry, sand as required. Finish same as new wood.



# Mixing Instructions: PRODUCT MUST BE CATALYZED.

Mix material thoroughly before and during use. Material may be mixed by hand or mechanical agitation at moderate speed. **To Catalyze:** Material should be agitated slowly while mixing in the catalyst. Mix or agitate thoroughly after adding catalyst before use (5-10 minutes). This product has been short-filled to allow room for both colorant and catalyst. Tint to desired color and catalyze as follows:

Short filled Gallon: Add 11.6 oz CAT10-0700 (Use supplied pre-measured bottle) to the short-filled gallon.

Short filled Five Gallon Pails: Add 58 oz of CAT10-0700 to the short-filled pail.

OR:

Mix 100 parts ASTW-10XX to 11 parts CAT10-0700 (11% by volume). This ratio refers to catalyst added to un-tinted product.

Mixing Chart (examples for mixing various amounts):

ASTW-10XX	<u>CAT10-0700</u>
128 oz	14 oz
100 oz	11 oz
27 oz	3 oz
9 oz	1 oz



#### Application:

Using conventional, HVLP, airless, or air assisted equipment, apply this product at 3-4 wet mils per coat. Let dry a minimum of 50-60 minutes. Sand with 280-320 grit, no-fill sandpaper and remove sanding dust with clean compressed air, or tack rag. This product must be sanded in between coats to ensure proper adhesion.

On wood substrates we recommend a coating system comprised of one coat of primer applied at 4-5 mils wet film build and 1-2 coats of topcoat applied at 4-5 mils wet film build. On MDF we recommend two coats of primer (especially on routed areas) applied at 4-5 mils wet film build and 1-2 coats of topcoat. Please refer to the Approved Companion Products section of this document for a list of companion primers.

This product may also be used as a self-seal system. Used as a self-seal system, we recommend 2-3 coats applied at 3-4 wet mils per coat. Maximum dry film thickness of the complete system **must not exceed 7 dry mils.** 



#### Recommended Tip Sizes:

Conventional Air
HVLP
1.9-2.1 mm
Airless
10-13 thousandths
Air Assisted Airless
11-13 thousandths



#### Precautions:

These products are intended for Professional use only. Do not proceed if you are planning on mixing with other finishing systems or other manufacturer's products. Gemini will not be held liable for finish failures due to the improper use of our products or deviation from our finishing recommendations.

#### Equipment:

All equipment used with this product must have plastic, stainless steel, or Teflon fluid passages and wetted parts.

#### Containers

We supply this material in a lined container. All containers used in conjunction with storage and/or application of this product must be stainless steel, plastic, or otherwise acid resistant.

#### Clean up:

Use SOL-9011 Non HAPs Thinner or SOL-9059 HAPs Free Reducer to clean up all equipment. Dispose of in accordance with Federal, State, and Local regulation regarding pollution.

Care and cleaning of this finish: Use a mild dishwashing liquid and a damp cloth to remove food, grease, and other residue. Wipe dry. Do not use cleaners that contain ammonia, bleach, or abrasives as this may damage the finish.