

PRODUCT DATA SHEET

White Pre-cat Lacquer-550 VOC

DESCRIPTION

The PCW550-10XX series is a high quality, white pre-catalyzed lacquer formulated for 550 VOC applications. These products are catalyzed at the factory and exhibit excellent chemical and moisture resistance. All products in this series pass the performance requirements established by the Kitchen Cabinet Manufactures Association (KCMA). For wood substrates only. For interior use only.

PRODUCT NUMBERS / SHEENS	COATING PROPERTIES	PREPARATION INSTRUCTIONS
PCW550-1060 Semi-Gloss	Viscosity: 23-27 #4 Ford Weight Solids: 39.6-40.1 %	Catalyzation: This product comes pre- catalyzed. Do NOT add catalyst.
PCW550-1030 Satin PCW550-1010 Flat	Volume Solids: 23.9-24.3 % Weight/Gallon: 8.6 lbs./gal Coverage: 384-389 sq. ft. per gallon at one mil dry film thickness. VOC (reg./coating): 4.25-4.29 lbs./gl. or 510- 514g/l	Reduction: Thinning: This product is supplied ready to spray for most applications. If needed due to conditions in your facility, or for
 PRODUCT ADVANTAGES > 550 VOC > Low HAPs > Water And Hammehold Observed 	VOC (actual/material): 2.64-2.66 lbs./gl. or 317-318g/l VOC Ratio: 0.77078 lbs. VOC/lbs. solids HAPS Ratio: 0.12 lbs. HAPS/lbs. solids	certain types of spray equipment, use SOL-9032 Non HAPs/Non VOC Thinner at levels not to exceed 10% by volume* VOC after this thinning recommendation is less than 550 grams per liter.
 Water And Household Chemical Resistant Ready to Spray Controlled Tint Base Short Filled For Easy Tinting Meets KCMA Requirements When Applied To Manufacturers Specifications. Non Photo Chemically Reactive Phthalate Free 	 Dry Times: Air Dry: at 78°F, relative humidity 50% To touch: 10 minutes To Handle: 30 minutes To sand/recoat: 45 minutes Force Dry: Flash: 8-10 minutes Bake: 15 @110°F minutes Cool down: 10 minutes Stack: 1 hour after cool down Relative humidity will affect the speed of drying. Ideal conditions are 75°F or warmer at 50% humidity or less. Dry time will be faster at higher temperatures and lower humidity and equally slower at colder temperatures and higher humidity. Dry Film Thickness: Maximum DFT for the complete system must not exceed 5 mils. Shelf Life: 12 months @77° F if unopened and stored in a cool dry area. Always rotate stock. 	Retarder: If a slower dry time is desired, or to prevent blushing in humid weather use SOL-9012 HAPs Free Retarder at levels not to exceed 4 oz per gallon (3% by volume)* VOC after this recommendation is less than 550 grams per liter. Note: Effective dry times will be lengthened if retarder is added Tinting: This product may be tinted up to 4 oz per gal with 844 colorants. Do not use umber pigments. Never tint with Universal Colorants that contain Glycol. *Thinning this material may result in increasing the VOC levels of this product. Refer to your local regulations before thinning. <u>Approved Companion Products</u> NEXP-7000 NEXPRIME Pre-cat Primer
work, but they may be used for comparison. To the best of our knowledge, the above technical data is true and accurate at the date of issuance but is subject to change without prior notice.		

February, 2023

The following supersedes any provision contained in the forms, letters and papers of your company. This product is designed and intended for professional application only. All products should be thoroughly tested under application conditions prior to use. The information contained herein is believed to be reliable. HOWEVER, GEMINI MAKES NO WARRANTY CONCERNING THIS PRODUCT, WHETHER EXPRESS OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. UNDER NO CIRCUMSTANCES SHALL GEMINI BE LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL, OR ANY OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH OF WARRANTY, STRICT LIABILITY, OR ANY OTHER LEGAL THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. THE SOLE REMEDY OF THE BUYER AND THE SOLE LIABLE TOR SOLE REMEDY OF THE BUYER AND THE SOLE LIABLITY OF GEMINI FOR ANY CLAIMS SHALL BE LIMITED TO THE BUYER'S PURCHASE PRICE OF THE PRODUCT WHICH IS THE SUBJECT OF THE CLAIM OR THE AMOUNT ACTUALLY PAID FOR SUCH PRODUCT, WHICHEVER IS LESS. TECHNICAL ADVICE FURNISHED BY GEMINI SHALL NOT CONSTITUTE AN EXPRESS WARRANTY, WHICH IS EXPRESSLY DISCLAIMED. ALL TECHNICAL ADVICE GIVEN IS ACCEPTED AT THE RISK OF THE BUYER. CAUTION: DANGER! FLAMMABLE! VAPORS MAY CAUSE FLASH FIRE. VAPOR HARMFUL. HARMFUL OR FATAL IF SWALLOWED. INJURIOUS TO EYES. KEEP OUT OF THE REACH OF CHILDREN! BEFORE using this product it is essential that the "Material Safety Data Sheet" describing the product as well as the "Product Label" be reviewed. If your company does not have such information or has any questions, contact the manufacturer.

PRODUCT DATA SHEET PCW550-10XX SERIES CONTINUED

A **I**A Substrate preparation:

New wood: Remove any dirt, grease, glue or other contaminants. Moisture content of wood should be 7-9%. Sand to 150-180 grit. Proper sanding of wood is absolutely critical to achieve the best color development and adhesion of the coating to the substrate.

Old wood: Strip old finishes completely and remove all contaminants from the surface. Make sure the surface is dry, sand as required. Finish same as new wood.



Mixing Instructions:

Mix material thoroughly before and during use. Material may be mixed by hand or mechanical agitation at moderate speed.



Application:

Using conventional, HVLP, airless, or air assisted equipment, apply this product at 3-4 wet mils per coat. Let dry a minimum of 45 minutes. Sand with 280-320 grit, no-fill sandpaper and remove sanding dust with clean compressed air, or tack rag. This product must be sanded in between coats to ensure proper adhesion.

This product may be used in conjunction with a pre-catalyzed primer, or used as a self-seal system.

If a primer is desired, we recommend a coating system comprised of one coat of primer applied at 3-3.5 mils wet film build and 2 coats of topcoat applied at 3-4 mils wet film build. Please see the approved companion products section of this document for approved primers.

If used as a self seal system we recommend 2-3 coats of PCW550-10XX series. Maximum dry film thickness of the complete system must not exceed 5 dry mils.



Recommended Tip Sizes:		
Conventional Air	1.8 mm	
HVLP	1.7-1.9 mm	
Airless	10-13 thousandths	
Air Assisted Airless-	11-13 thousandths	



Precautions:

These products are intended for Professional use only. Do not proceed if you are planning on mixing with other finishing systems or other manufacturer's products. Gemini will not be held liable for finish failures due to the improper use of our products or deviation from our finishing recommendations

Equipment:

All equipment used with this product must have plastic, stainless steel, or Teflon fluid passages and wetted parts

Containers:

We supply this material in a lined container. All containers used in conjunction with storage and/or application of this product must be stainless steel, plastic, or otherwise acid resistant.

Clean up:

Use SOL-0020 Acetone, or SOL-9032 Zero VOC Lacquer Thinner to clean up all equipment. Dispose of in accordance with Federal, State, and Local regulation regarding pollution.

Care and cleaning of this finish: Use a mild dishwashing liquid and a damp cloth to remove food, grease, and other residue. Wipe dry. Do not use cleaners that contain ammonia, bleach, or abrasives as this may damage the finish.