

PRODUCT DATA SHEET

Waterborne Lacquer Clear

DESCRIPTION

Gemini's WBXL-03XX series is a single component, self-crosslinking, clear waterborne lacquer. This product can be used on interior woodwork in areas where extreme water and chemical resistance are not necessary. It has very good hardness and durability, is water clear, and has excellent resistance to yellowing. For wood substrates only. For interior use only.

PRODUCT NUMBERS / SHEENS	COATING PROPERTIES	PREPARATION INSTRUCTIONS
WBXL-0390 Gloss WBXL-0360 Semi-Gloss	Viscosity: 30"-35" #3 Zahn @ 77° Weight Solids: 32.2-34.3% Volume Solids: 29.5-30.9% Weight/Gallon: 8.5-8.67 lbs./gal	Reduction/Thinning*: Reduction is not necessary but may be required for certain types of application and equipment. Use water
WBXL-0330 Satin	Coverage: 473-496 sq. ft. per gallon at one mil dry	for reduction. Very little water is needed to reduce viscosity, typically no more than 5% by
WBXL-0320 Dull	film thickness.	volume.
WBXL-0310 Flat	VOC (reg./coating): 1.57-1.66 lbs./gal or 187.9- 198.4 g/l VOC (act/material): .6163 lbs./gal or 73.2-75 g/l VOC Ratio: 0.2-0.23 lbs. VOC/lbs. Solids	Retarder: If a slower dry time is desired, or to improve flow and leveling, use SOL-0090 at levels not to exceed 4% by volume (5.1 oz per gallon). Maximum VOC when adding retarder
Product Advantages	HAPS Ratio: 0.0 lbs. HAPS/lbs. Solids	as specified is < 275 grams per liter.
➤ Low Odor	Dry Times:	
Dries fast	Air Dry: at 78° F, relative humidity 50% To touch: 10-12 minutes	*Thinning this material may result in
➤ Water Clear	To handle: 15-20 minutes	increasing the VOC levels of this product.
➤ Excellent Resistance To	To sand/recoat: 35-45 minutes Force Dry:	Refer to your local regulations before thinning.
Yellowing*	Flash: 10 minutes Bake: 30 min @ 105° F	
Durable Film	Cool down: 10 min	
➤ Superb Flow And Leveling		Approved Companion Products WBXLSS-0100 EVO® Sanding Sealer
Minimal Grain Raise	Relative humidity will affect the speed of drying. Ideal conditions are 75° F or warmer at 50% humidity or less. Dry time will be faster at higher	
➤ Low VOC And HAPs Free		
➤ Formaldehyde Free	temperatures and lower humidity and equally slower at colder temperatures and higher humidity.	
➤ Phthalate Free	,	
* The coating will not protect the wood, lightly stained wood substrates, or pigmented	Dry Film Thickness: Maximum DFT for a complete system must not exceed 6 dry mils.	
basecoats from yellowing	Shelf Life: 18 months @77° F if unopened and stored in a cool dry area. Always rotate stock. Storage: Protect product from freezing.	
	Note: These numbers represent actual control values on a smooth, sanded substrate. Spray techniques, texture, and sealing as well as film thickness may give different results on actual work, but they may be used for comparison. To the best of our knowledge, the above technical data is true and accurate at the date of issuance but is subject to change without prior notice.	

February, 2023

The following supersedes any provision contained in the forms, letters and papers of your company. This product is designed and intended for professional application only. All products should be thoroughly tested under application conditions prior to use. The information contained herein is believed to be reliable. HOWEVER, GEMINI MAKES NO WARRANTY CONCERNING THIS PRODUCT, WHETHER EXPRESS OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. UNDER NO CIRCUMSTANCES SHALL GEMINI BE LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL, OR ANY OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH OF WARRANTY, STRICT LIABILITY, OR ANY OTHER LEGAL THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. THE SOLE REMEDY OF THE BUYER AND THE SOLE LIABILITY OF GEMINI FOR ANY CLAIMS SHALL BE LIMITED TO THE BUYER'S PURCHASE PRICE OF THE PRODUCT WHICH IS THE SUBJECT OF THE CLAIM OR THE AMOUNT ACTUALLY PAID FOR SUCH PRODUCT, WHICHEVER IS LESS. TECHNICAL ADVICE FURNISHED BY GEMINI SHALL NOT CONSTITUTE AN EXPRESS WARRANTY, WHICH IS EXPRESSLY DISCLAIMED. ALL TECHNICAL ADVICE GIVEN IS ACCEPTED AT THE RISK OF THE BUYER. CAUTION: DANGER! FLAMMABLE! VAPORS MAY CAUSE FLASH FIRE. VAPOR HARMFUL. HARMFUL OR FATAL IF SWALLOWED. INJURIOUS TO EYES. KEEP OUT OF THE REACH OF CHILDREN! BEFORE using this product it is essential that the "Material Safety Data Sheet" describing the product as well as the "Product Label" be reviewed. If your company does not have such information or has any questions, contact the manufacturer.

PRODUCT DATA SHEET WBXL-03XX SERIES CONTINUED



New wood: Remove any dirt, grease, glue or other contaminants. Moisture content of wood should be 7-9%. Sand to 150-180 grit. Proper sanding of wood is absolutely critical to achieve the best color development and adhesion of the coating to the substrate.

Old wood: Strip old finishes completely and remove all contaminants from the surface. Make sure the surface is dry, sand as required. Finish same as new wood.

Mixing Instructions:

Mix thoroughly before use. DO NOT SHAKE! Material may be mixed by hand or mechanical agitation at moderate speed.



Application:

Using conventional, HVLP, airless, or air assisted equipment, apply this product at 3-4 wet mils per coat. Let dry a minimum of 35-45 minutes. Sand with 280-320 grit, no-fill sandpaper and remove sanding dust with clean compressed air. This product must be sanded in between coats to ensure proper adhesion.

This product has been designed as a self-seal system. Typically, we recommend a coating system comprised of 2-3 coats WBXL-03XX applied at 3-4 wet mils. If used with a sealer we recommend a coating system comprised of 1 coat of WBXLSS-0100 sealer applied at 3-4 wet mils per coat and 1-2 coats of WBXL-03XX. **Maximum dry film thickness of the complete system must not exceed 6 dry mils.**

This product must not be polluted with oil, solvent based paint or the like and should not be applied to metal surfaces. Application and drying conditions must be at temperatures of 60°F or above and at a humidity of less than 65%. Increased air flow and/or drying temperatures, including the use of infrared lighting for cure will significantly decrease dry times.



Recommended Tip Sizes:

Conventional Air 1.8-2.0 mm HVLP 1.9-2.2 mm

Airless 10-13 thousandths
Air Assisted Airless- 11-13 thousandths



Precautions:

These products are intended for Professional use only. Do not proceed if you are planning on mixing with other finishing systems or other manufacturer's products. Gemini will not be held liable for finish failures due to the improper use of our products or deviation from our finishing recommendations

Equipment:

All equipment used with this product must have plastic, stainless steel, or Teflon fluid passages and wetted parts

Containers:

All containers used in conjunction with storage and/or application of this product should be stainless steel or plastic to avoid rust.

Clean up:

Use water to clean all equipment when material is in a liquid stage. Use 2:1 mixture of water and Butyl Cellosolve (SOL-0061) to remove semi-dried or dried coating. Dispose of in accordance with Federal, State, and Local regulation regarding pollution.

Care and cleaning of this finish: Use a mild dishwashing liquid and a damp cloth to remove food, grease, and other residue. Wipe dry. Do not use cleaners that contain ammonia, bleach, or abrasives as this may damage the finish.